

POLYPROPYLENE LAMINATE PRODUCT PROPERTIES

- Polypropylene
- Spunbond
- Binder N/A
- Good Chemical Compatibility
- Low Cost
- High Strength
- Good Efficiency

FSP#	WEIGHT (O.S.Y.)	THICK (MILS)	GRAB STRENGTH		PERM (CFM)
			MACHINE DIRECT	CROSS DIRECT	
SPB30LAM	1.50	14	44	35	258
SPB40LAM	2.00	19	70	50	219
SPB50LAM	2.50	21	>90	75	172
SPB60LAM	3.00	26	>100	85	150



Filtration Systems Products, Inc.
8506 Herrington Ct.
Pevely, MO 63070 USA

Phone 1.314.721.2888
Fax 1.314.721.4519

www.fsptbm.com

This information is provided only as a general guide as to the likely properties of the product and neither FSP nor any of its divisions assumes any responsibility or liability whatsoever for the accuracy or completeness of the information contained herein nor do we undertake to notify any recipient of any changes of this information. The final determination of the suitability of this product for any application and whether its use in any application constitutes an infringement of any part or other intellectual property right is the sole responsibility of the user. Users of the product should satisfy themselves by independent investigation that it can be used safely to meet any specific functional requirements for any desired application.