

CEREX PB

PRODUCT PROPERTIES

FIBER: Nylon
CONSTRUCTION: Spunbond
BONDING: Pointbond

FSP #	Weight (O.S.Y.)	Thick (mils)	Mullen Burst (PSI) ASTM D3786	Tensile Strength (ft/lbs) ASTM D5034		Perm (CFM) ASTM D737-75
				Machine Direct	Cross Direct	
SB06PB	0.3	3.9	8	6	3	1350
SB10PB	0.5	5.5	13	13	8	1000
SB14PB	0.7	7.2	19	20	12	825
SB17PB	0.85	8	24	25	17	700
SB20PB	1.0	9	28	31	21	600
SB30PB	1.5	12.2	44	52	36	375
SB40PB	2.0	14.2	61	75	52	275
SB60PB	3.0	18.4	97	122	86	150
SB80PB	4.0	21.8	117	156	118	110



Filtration Systems Products, Inc.
1.314.721.2888
8506 Herrington Ct.
Pevely, MO 63070 USA

Phone

Fax 1.314.721.4519

www.fsptbm.com

This information is provided only as a general guide as to the likely properties of the product and neither FSP nor any of its divisions assumes any responsibility or liability whatsoever for the accuracy or completeness of the information contained herein nor do we undertake to notify any recipient of any changes of this information. The final determination of the suitability of this product for any application and whether its use in any application constitutes an infringement of any part or other intellectual property right is the sole responsibility of the user. Users of the product should satisfy themselves by independent investigation that it can be used safely to meet any specific functional requirements for any desired application.

Revision B: 9/23/2015

