

MANNIWEB

PRODUCT PROPERTIES

FIBER: Polyester/Cellulose
CONSTRUCTION: Wetform
BONDING: Chemical Binder

FSP #	Weight (O.S.Y.)	Thick (mils)	Mullen Burst (PSI) ASTM D3786	Tensile Strength (ft/lbs) ASTM D5034		Perm (CFM) ASTM D737-75
				Machine Direct	Cross Direct	
SMW20	1.0	9	36	43	28	532
SMW30	1.5	14	55	47	30	419
SMW36	1.8	16	63	60	40	351
SMW50	2.5	20	72	77	57	164
SMW70	3.5	26	108	115	95	124



Filtration Systems Products, Inc.
8506 Herrington Ct.
Pevely, MO 63070 USA

Phone 1.314.721.2888
Fax 1.314.721.4519
www.fsptbm.com

This information is provided only as a general guide as to the likely properties of the product and neither FSP nor any of its divisions assumes any responsibility or liability whatsoever for the accuracy or completeness of the information contained herein nor do we undertake to notify any recipient of any changes of this information. The final determination of the suitability of this product for any application and whether its use in any application constitutes an infringement of any part or other intellectual property right is the sole responsibility of the user. Users of the product should satisfy themselves by independent investigation that it can be used safely to meet any specific functional requirements for any desired application.