

# REEMAY

## PRODUCT PROPERTIES

FIBER: Polyester  
CONSTRUCTION: Spunbond  
BONDING: Flatbond

FSP #	Weight (O.S.Y.)	Thick (mils)	Mullen Burst (PSI) ASTM D3786	Tensile Strength (ft/lbs) ASTM D5034		Perm (CFM) ASTM D737-75
				Machine Direct	Cross Direct	
SLB10	0.50	5	7	9.0	7.0	1170
SLB12	0.60	8	11	10.0	8.0	1067
SLB14	0.75	9	12	14.0	11.0	1021
SLB16	0.75	8	15	19.0	14.0	1064
SLB20	1.00	10	17	19.0	16.0	893
SLB28	1.35	12	32	36.0	27.0	681
SLB28F	1.35	12	28	32	30	521
SLB44	2.10	12	52	61.0	47.0	385
SLB60	2.95	18	84	102.0	78.0	287
SLB80	4.00	20	100	125.0	100.0	190
SLB120	6.00	31	82	136.0	100.0	176
SLB40LAM	2.00	8.6	51	61	44	215
SLB60LAM	3.00	12	75	105	75	145



FILTRATION SYSTEMS PRODUCTS, INC.

8506 Herrington Ct.  
Pevely, MO 63070  
(314) 721-2888  
(314) 721-4519

809 South Main St.  
Fredericktown, MO 63645  
(800) 444-4720  
(573) 783-6334

150 22<sup>nd</sup> Street  
Moline, IL 61265  
(309) 736-7351  
(309) 736-7352

[www.fsptbm.com](http://www.fsptbm.com)

This information is provided only as a general guide as to the likely properties of the product and neither FSP nor any of its divisions assumes any responsibility or liability whatsoever for the accuracy or completeness of the information contained herein nor do we undertake to notify any recipient of any changes of this information. The final determination of the suitability of this product for any application and whether its use in any application constitutes an infringement of any part or other intellectual property right is the sole responsibility of the user. Users of the product should satisfy themselves by independent investigation that it can be used safely to meet any specific functional requirements for any desired application.

Revision: E 04/23/2018