

POLYESTER SPUNBOND (TYPE III) PRODUCT PROPERTIES

- Polyester
- Spunbond/Flatbond
- Binder N/A
- High Strength
- Chemical Resistance
- High Flow Rates

| FSP# | WEIGHT (O.S.Y.) | THICK (MILS) | GRAB STRENGTH | | MULLEN BURST | PERM (CFM) |
|----------|--------------------|-----------------|-------------------|-----------------|-----------------|---------------|
| | | | MACHINE DIRECT | CROSS DIRECT | | |
| S-MP11FB | .59 | 7 | 14 | 6 | 55 | 1141 |
| S-MP12FB | .60 | 7 | 15 | 7 | 52 | 996 |
| S-MP15FB | .75 | 7 | 17 | 11 | 62 | 937 |
| S-MP20FB | 1.0 | 8 | 24 | 16 | 77 | 736 |
| S-MP25FB | 1.25 | 10 | 32 | 20 | 76 | 623 |
| S-MP30FB | 1.5 | 11 | 36 | 25 | 104 | 553 |
| S-MP35FB | 1.75 | 11 | 41 | 37 | 115 | 475 |
| S-MP40FB | 2.0 | 13 | 53 | 38 | 129 | 416 |
| S-MP50FB | 2.5 | 13 | 59 | 44 | 131 | 278 |
| S-MP60FB | 3.0 | 14 | 64 | 49 | 140 | 276 |
| S-MP80FB | 4.0 | 19 | 68 | 60 | 80 | 191 |
| | | | | | | |



Filtration Systems Products, Inc.
8506 Herrington Ct.
Pevely, MO 63070 USA

Phone 1.314.721.2888
Fax 1.314.721.4519
www.fsptbm.com

This information is provided only as a general guide as to the likely properties of the product and neither FSP nor any of its divisions assumes any responsibility or liability whatsoever for the accuracy or completeness of the information contained herein nor do we undertake to notify any recipient of any changes of this information. The final determination of the suitability of this product for any application and whether its use in any application constitutes an infringement of any part or other intellectual property right is the sole responsibility of the user. Users of the product should satisfy themselves by independent investigation that it can be used safely to meet any specific functional requirements for any desired application.